

P24007.A10



Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (original) An antimicrobial wound covering article, wherein at least a part of the article comprises a polyurethane resin which is associated with a particulate, silver containing glass, said glass being capable of releasing silver ions when coming into contact with a wound exudate.
2. (original) The article of claim 1, wherein at least a part of the polyurethane resin forms a matrix which comprises at least a part of the particulate glass.
3. (original) The article of claim 1, wherein at least a part of the particulate glass is present on a surface of a structure which comprises the polyurethane resin.
4. (original) The article of claim 1, wherein at least a part of the polyurethane resin forms a sheet-like structure.
5. (original) The article of claim 1, wherein at least a part of the polyurethane resin comprises a polyurethane foam.

P24007.A10

6. (original) The article of claim 4, wherein at least a part of the polyurethane resin is not foamed.

7. (original) The article of claim 1, wherein the polyurethane resin forms a gel-like material.

8. (original) The article of claim 7, wherein at least a part of an external surface of the article comprises the polyurethane resin.

9. (original) The article of claim 4, wherein at least a part of the polyurethane resin and at least a part of the particulate glass form a layer which has an area weight of from about 400 g/m² to about 1200 g/m².

10. (original) The article of claim 2, wherein at least a part of the polyurethane resin and at least a part of the particulate glass form a sheet-like layer having a thickness of from about 0.1 mm to about 2 mm.

11. (original) The article of claim 6, wherein at least a part of the polyurethane resin and at least a part of the particulate glass form a layer having a thickness of from about 0.4 mm to about 1.5 mm.

12. (original) The article of claim 1, wherein at least a part of the polyurethane resin and at

P24007.A10

least a part of the particulate glass form a sheet-like layer having a thickness of from about 0.6 mm to about 1.2 mm.

13. (original) The article of claim 9, wherein the polyurethane resin has a liquid absorption capacity of from about 0.5 g/g to about 10 g/g.

14. (original) The article of claim 8, wherein the polyurethane resin has a liquid absorption capacity of from about 1 g/g to about 6 g/g.

15. (original) The article of claim 11, wherein the polyurethane resin has a liquid absorption capacity of from about 1.5 g/g to about 3.5 g/g.

16. (original) The article of claim 9, wherein the layer has a water vapor permeability of from about $100 \text{ g}/(\text{m}^2 \cdot 24\text{h})$ to about $5,000 \text{ g}/(\text{m}^2 \cdot 24\text{h})$.

17. (original) The article of claim 10, wherein the layer has a water vapor permeability of from about $250 \text{ g}/(\text{m}^2 \cdot 24\text{h})$ to about $2,500 \text{ g}/(\text{m}^2 \cdot 24\text{h})$.

18. (original) The article of claim 11, wherein the layer has a water vapor permeability of from about $300 \text{ g}/(\text{m}^2 \cdot 24\text{h})$ to about $1,500 \text{ g}/(\text{m}^2 \cdot 24\text{h})$.

19. (original) The article of claim 8, wherein the polyurethane resin is self-adhesive.

P24007.A10

20. (original) The article of claim 1, wherein the polyurethane resin comprises a pigment.

21. (original) The article of claim 20, wherein the pigment comprises TiO_2 .

22. (original) The article of claim 21, wherein the TiO_2 is present in an amount of from about 0.01 % by weight to about 2 % by weight, based on the weight of the polyurethane resin.

23. (original) The article of claim 1, wherein the article further comprises a superabsorber.

24. (original) The article of claim 23, wherein the superabsorber is present in an amount of from about 0.5 % by weight to about 30 % by weight, based on the weight of the polyurethane resin.

25. (original) The article of claim 1, wherein the polyurethane comprises units which are derived from a polyol component which comprises at least one polyether polyol.

26. (original) The article of claim 25, wherein the at least one polyether polyol comprises from about 2 to about 6 hydroxy groups.

27. (original) The article of claim 26, wherein the at least one polyether polyol has a hydroxy number of from about 20 to about 120.

P24007.A10

28. (original) The article of claim 27, wherein the at least one polyether polyol comprises at least about 10 % by weight of units which are derived from ethylene oxide.

29. (original) The article of claim 26, wherein the at least one polyether polyol comprises units which are derived from ethylene oxide, propylene oxide and at least one compound having more than two hydroxy groups.

30. (original) The article of claim 29, wherein the at least one compound comprises pentaerythritol.

31. (original) The article of claim 25, wherein the at least one polyether polyol has a weight average molecular weight of from about 2,000 to about 8,000.

32. (original) The article of claim 1, wherein the polyurethane comprises units which are derived from a polyisocyanate component which comprises at least one aliphatic polyisocyanate.

33. (original) The article of claim 32, wherein the aliphatic polyisocyanate comprises at least one polymethylene diisocyanate which has from about 2 to about 8 methylene groups.

34. (original) The article of claim 33, wherein the aliphatic diisocyanate comprises

P24007.A10

hexamethylene diisocyanate.

35. (original) The article of claim 2, wherein the polyurethane comprises units which are derived from at least one polyether polyol and at least one aliphatic diisocyanate.

36. (original) The article of claim 35, wherein the at least one polyether polyol comprises from about 2 to about 6 hydroxy groups, has a hydroxy number of from about 20 to about 120 and comprises at least about 10 % by weight of units which are derived from ethylene oxide.

37. (original) The article of claim 36, wherein the at least one aliphatic diisocyanate comprises hexamethylene diisocyanate.

38. (original) The article of claim 1, wherein a ratio of a number of free isocyanate groups in a polyisocyanate starting material to a number of free hydroxy groups in a polyol starting material for producing the polyurethane is in the range of from about 0.3 to about 0.7.

39. (original) The article of claim 1, wherein a product of a functionality of a polyisocyanate starting material and a functionality of a polyol starting material for producing the polyurethane is at least about 5.2.

40. (original) The article of claim 1, wherein the glass comprises particles having a volume-

P24007.A10

related particle size of from about 0.1 μm to about 10 μm .

41. (original) The article of claim 1, wherein the glass comprises glass fibers.

42. (original) The article of claim 40, wherein the glass comprises not more than about 5 % by weight of residual water.

43. (original) The article of claim 40, wherein the glass comprises about 40-60 mole-% of P_2O_5 , about 35-55 mole-% of at least one of CaO , MgO , ZnO and CuO , up to about 5 mole-% of at least one of Na_2O , K_2O and Li_2O , and about 5-20 mole-% of at least one of SiO_2 , Al_2O_3 and B_2O_3 , and contains from about 0.1 % by weight to about 8 % by weight of Ag_2O .

44. (original) The article of claim 42, wherein the glass comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of at least one of CaO and MgO , up to about 5 mole-% of at least one of Na_2O and K_2O , and about 5-10 mole-% of at least one of SiO_2 and Al_2O_3 , and contains from about 0.5 % by weight to about 5 % by weight of Ag_2O .

45. (withdrawn) The article of claim 2, wherein the glass comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of MgO , and about 5-10 mole-% of at least one of SiO_2 and Al_2O_3 , and contains from about 1% by weight to about 3 % by weight of Ag_2O .

P24007.A10

46. (withdrawn) The article of claim 1, wherein the glass comprises about 49-51 mole-% of P_2O_5 , about 43-45 mole-% of MgO , and about 5-7 mole-% of Al_2O_3 , and contains from about 1.5 % by weight to about 2.5 % by weight of Ag_2O .

47. (original) The article of claim 9, wherein the glass is present in an amount of from about 0.01 % by weight to about 40 % by weight, based on the combined weight of the glass and the polyurethane resin.

48. (original) The article of claim 43, wherein the glass is present in an amount of from about 0.05 % by weight to about 10 % by weight, based on the combined weight of the glass and the polyurethane resin.

49. (original) The article of claim 1, wherein the glass is present in an amount of from about 0.1 % by weight to about 5 % by weight, based on the combined weight of the glass and the polyurethane resin.

50. (original) The article of claim 1, wherein the article is capable of releasing silver ions for at least about 10 hours when in contact with a wound exudate.

51. (original) The article of claim 48, wherein the article is capable of releasing silver ions for at least about 24 hours when in contact with a wound exudate.

P24007.A10

52. (original) The article of claim 49, wherein the polyurethane resin comprises at least one of elemental Al, Zn, Mg and basic compounds thereof.

53. (original) The article of claim 52, wherein said at least one of elemental Al, Zn, Mg and basic compounds thereof is present in an amount of from about 0.01 % by weight to about 5 % by weight, based on the weight of the polyurethane resin.

54. (original) The article of claim 49, wherein the glass contains from about 0.5 to about 2.5 % by weight of Ag_2O .

55. (withdrawn) The article of claim 1, wherein the polyurethane comprises units which are derived from at least one polyether polyol and at least one aliphatic diisocyanate, and wherein the glass comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of MgO , and about 5-10 mole-% of at least one of SiO_2 and Al_2O_3 , and contains from about 1 % by weight to about 3 % by weight of Ag_2O .

56. (original) The article of claim 1, wherein the article further comprises a backing material.

57. (original) The article of claim 56, wherein the backing material comprises a polyurethane.

P24007.A10

58. (original) The article of claim 57, wherein the backing material comprises a polyurethane sheet having a pressure sensitive adhesive on a side thereof which faces the polyurethane resin which is associated with the glass.

59. (original) The article of claim 58, wherein the polyurethane sheet is substantially transparent.

60. (original) The article of claim 56, wherein the article is a bandage.

61. (original) The article of claim 59, wherein the article is a bandage.

62. (original) The article of claim 1, wherein the article is one of a wound dressing, a wound pad and a compress.

63. (original) The article of claim 43, wherein the article releases silver at a rate of from about $5 \text{ mg}/(\text{m}^2 \cdot 24\text{h})$ to about $50 \text{ mg}/(\text{m}^2 \cdot 24\text{h})$.

64. (original) The article of claim 1, wherein the article releases silver at a rate of from about $10 \text{ mg}/(\text{m}^2 \cdot 24\text{h})$ to about $40 \text{ mg}/(\text{m}^2 \cdot 24\text{h})$.

65. (original) The article of claim 1, wherein the polyurethane resin comprises the residue of a Bi containing catalyst.

P24007.A10

66. (original) The article of claim 2 wherein the polyurethane resin has been formed by reacting at least one polyol and at least one polyisocyanate in the presence of the particulate glass.

67. (withdrawn) The article of claim 1, wherein the polyurethane comprises units which are derived from hexamethylene diisocyanate and units which are derived from at least one polyether polyol having a hydroxy number of from about 20 to about 120 and comprising at least about 10 % by weight of ethylene oxide units, wherein the particulate glass has a volume-related particle size of from about 0.1 μm to about 10 μm , comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of MgO , and about 5-10 mole-% of Al_2O_3 , and contains from about 1 % by weight to about 3 % by weight of Ag_2O , and wherein the polyurethane resin forms a matrix which contains about 0.1 % by weight to about 5 % by weight of the glass, based on the combined weight of the glass and the polyurethane.

68. – 97. (cancelled)

98. (original) The article of claim 1, wherein the article does not show a noticeable discoloration after having been kept at 50 °C for 6 months.

99. (original) The article of claim 67, wherein the article does not show a noticeable discoloration after having been kept at 50 °C for 6 months.

P24007.A10

100. (original) The article of claim 1, wherein the article does not show a noticeable discoloration after having been sterilized with 26 kGy of γ -rays.

101. (currently amended) The article of claim 1, wherein the article shows an antimicrobial activity against *Escherichia coli* IFO 3972, tested according to JIS 2801:2000, of at least about 3.6, ~~when tested according to JIS 2801:2000~~.

102. (currently amended) The article of claim 1, wherein the article shows an antimicrobial activity against *Staphylococcus aureus*, tested according to JIS 2801:2000, of at least about 3.3, ~~when tested according to JIS 2801:2000~~.

103. (new) An antimicrobial wound covering article, wherein at least a part of the article comprises a polyurethane resin with a particulate, silver containing glass dispersed therein, said glass being capable of releasing silver ions when coming into contact with a wound exudate, the polyurethane resin comprising incorporated therein a superabsorber in an amount of from about 0.01 % to about 40 % by weight, based on the total weight of the polyurethane resin.

104. (new) The article of claim 103, wherein the superabsorber is selected from water-absorbing salts of polyacrylates and copolymers thereof.

105. (new) The article of claim 103, wherein the superabsorber comprises a crosslinked

P24007.A10

polymer based on acrylic acid/sodium acrylate.

106. (new) The article of claim 103, wherein the superabsorber is incorporated in the polyurethane resin in an amount of from about 0.5 % to about 30 % by weight, based on the total weight of the polyurethane resin.

107. (new) The article of claim 103, wherein at least a part of the polyurethane resin forms a sheet-like structure.

108. (new) The article of claim 103, wherein at least a part of the polyurethane resin comprises a polyurethane foam.

109. (new) The article of claim 103, wherein the polyurethane resin forms a gel-like material.

110. (new) The article of claim 107, wherein at least a part of the polyurethane resin and at least a part of the particulate glass form a layer having a thickness of from about 0.6 mm to about 1.2 mm.

111. (new) The article of claim 110, wherein the polyurethane resin has a liquid absorption capacity of from about 1.5 g/g to about 3.5 g/g.

P24007.A10

112. (new) The article of claim 111, wherein the layer has a water vapor permeability of from about 300 g/(m²*24h) to about 1,500 g/(m²*24h).

113. (new) The article of claim 103, wherein the polyurethane resin is self-adhesive.

114. (new) The article of claim 103, wherein the polyurethane resin comprises TiO₂ in an amount of from about 0.01 % by weight to about 2 % by weight, based on the weight of the polyurethane resin.

115. (new) The article of claim 103, wherein the polyurethane comprises units which are derived from a polyol component which comprises at least one polyether polyol.

116. (new) The article of claim 115, wherein the at least one polyether polyol has a hydroxy number of from about 20 to about 120 and comprises at least about 10 % by weight of units which are derived from ethylene oxide.

117. (new) The article of claim 116, wherein the at least one polyether polyol has a weight average molecular weight of from about 2,000 to about 8,000.

118. (new) The article of claim 115, wherein the polyurethane comprises units which are derived from a polyisocyanate component which comprises at least one aliphatic polyisocyanate.

P24007.A10

119. (new) The article of claim 103, wherein the glass comprises particles having a volume-related particle size of from about 0.1 μm to about 10 μm .

120. (new) The article of claim 119, wherein the glass comprises about 40-60 mole-% of P_2O_5 , about 35-55 mole-% of at least one of CaO , MgO , ZnO and CuO , up to about 5 mole-% of at least one of Na_2O , K_2O and Li_2O , and about 5-20 mole-% of at least one of SiO_2 , Al_2O_3 and B_2O_3 , and contains from about 0.1 % by weight to about 8 % by weight of Ag_2O .

121. (new) The article of claim 120, wherein the glass comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of at least one of CaO and MgO , up to about 5 mole-% of at least one of Na_2O and K_2O , and about 5-10 mole-% of at least one of SiO_2 and Al_2O_3 , and contains from about 0.5 % by weight to about 5 % by weight of Ag_2O .

122. (new) The article of claim 121, wherein the glass is present in an amount of from about 0.1 % by weight to about 5 % by weight, based on the combined weight of the glass and the polyurethane resin.

123. (new) The article of claim 122, wherein the glass contains from about 0.5 to about 2.5 % by weight of Ag_2O .

124. (new) The article of claim 103, wherein the article is a bandage.

P24007.A10

125. (new) The article of claim 103, wherein the article is one of a wound dressing, a wound pad and a compress.

126. (new) The article of claim 103, wherein the polyurethane resin has been formed by reacting at least one polyol and at least one polyisocyanate in the presence of the particulate glass.

127. (new) The article of claim 103, wherein the article does not show a noticeable discoloration after having been kept at 50 °C for 6 months.

128. (new) The article of claim 127, wherein the article does not show a noticeable discoloration after having been sterilized with 26 kGy of γ -rays .

129. (new) The article of claim 103, wherein the article shows an antimicrobial activity against *Escherichia coli* IFO 3972, tested according to JIS 2801:2000, of at least about 3.6.

130. (new) The article of claim 129, wherein the article shows an antimicrobial activity against *Staphylococcus aureus*, tested according to JIS 2801:2000, of at least about 3.3.

131. (new) An antimicrobial wound covering article, wherein at least a part of the article comprises a polyurethane resin with a particulate, silver containing glass dispersed therein, said glass being capable of releasing silver ions when coming into contact with a wound .

P24007.A10

exudate, the polyurethane resin having incorporated therein in an amount of from about 0.5 % to about 30 % by weight, based on the total weight of the polyurethane resin, a superabsorber which comprises a crosslinked polymer based on acrylic acid/sodium acrylate.

132. (new) The article of claim 131, wherein the glass is present in an amount of from about 0.1 % by weight to about 5 % by weight, based on the combined weight of the glass and the polyurethane resin, and comprises about 45-55 mole-% of P_2O_5 , about 40-50 mole-% of at least one of CaO and MgO, up to about 5 mole-% of at least one of Na_2O and K_2O , about 5-10 mole-% of at least one of SiO_2 and Al_2O_3 , and from about 0.5 % by weight to about 5 % by weight of Ag_2O .